

FlawGlo®

Product Data Sheet

FMI 800

Fluorescent Magnetic Ink

FMI 800 is an aerosol spray can containing OF 800 fluorescent yellow-green particles. It is designed to detect very fine discontinuities in finished products and critical, highly stressed components. Its ultra-bright, highly sensitive particles provide excellent flaw detection capability.

Appearance:

- Fluorescent yellow green powder suspended in petroleum distillate

Properties:

- Colour: Fluorescent Yellow Green
- Concentration: 1.25 g/litre
- Density : 0.820 g/ml
- Flashpoint : 100°C
- Processing Temperature: 0-49°C
- Particle Size: The typical range of particle sizes is from 2 to 5 µm, with an average particle size of 3 µm.
- Sensitivity: FMI 800 shows a minimum of 8 lines on AISI Ketos tool steel ring (as defined in SAE AS 5282), set on a 25mm diameter copper bar, magnetized with 2500 A of direct current.

Compliance & Specifications:

- IS 3703:2004
- ISO 9934-2
- AMS 3044
- API RP 5A5
- ASME B&PV
- MIL-STD-271
- MIL-STD-2132
- NAVSEA 250-1500-1
- ASTM E709
- ASTM E3024
- ASTM E1444

Application:

- For best results, use FMI 800 between 21°C and 32°C (70°F to 90°F) on thoroughly cleaned surfaces.
- Shake the can vigorously until the marble rattles, and occasionally during use.
- Spray the solution onto the magnetized surface from 7 to 12 inches (18 to 30 cm) at 45° angle until the surface is thoroughly covered with the solution.
- Examine the surface under black/UV-A light for fluorescent indications.
- If clogging develops, turn the spray button 1/4 turn. If clogging persists, remove and clean the spray button. Do not insert a pin or any other object into the can opening. Now, gently place the spray button with a twisting motion, holding the top of the can and pointing the spray button opening away from you.

Shelf Life:

Recommended to use within 24 months, the product can be used for next 3 years, if it satisfies spraying & performance parameters.

Pack Sizes: Aerosol Can (1box of 10 cans), each can with Net Qty 400 ml

Disclaimer: Our technical advice, information and statements given verbally, in writing or in the form of test results, are offered for your guidance without warranty. No warranty of fitness for a particular purpose is made. It is the user's responsibility to test the suitability of each product for his intended process and applications. Our guarantee is limited to the consistent quality of our products.